

DESCRIPTION

- ultra-premium, two component isocyanate cured, high solids polyurethane topcoat, with excellent gloss and flow.

PRINCIPAL CHARACTERISTICS

- excellent colour and gloss retention
- excellent resistance to exterior exposure
- tough, flexible and abrasion resistant
- unlimited recoatability with suitable preparation
- resistant to splash of mineral and vegetable oils, white spirit, paraffins and aliphatic petroleum products
- resistant to splash of mild chemicals
- can be air dried or force dried up to 60°C on metal to improve throughput

Note: we advise that you test this product to determine if it is suitable for your particular use.

COLOURS AND GLOSS

- white, AS2700 Colours
- colours obtained by tinting with Ultratint tinters
- full gloss

RECOMMENDED FILM THICKNESS (PER COAT)

	Minimum	Maximum	Typical
Dry film thickness microns	40	65	50
Wet film thickness microns	77	125	96
Theoretical spreading rate m ² /l	13.25	8.15	10.6

BASIC DATA AT 25 °C AND 50% RELATIVE HUMIDTY

- vehicle type..... polyurethane
- solids content approx..... 53 % by volume
- mix ratio 4A:1B by volume
- surface dry after 5-6 hrs
- hard dry after 10 hours
- full cure 7 days

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- best coating performance will be obtained with the highest degree of surface preparation
- degrease thoroughly to remove all oil, grease and other surface contaminants
- substrate temperature should be at least 3 °C above dew point
- relative humidity should not exceed 75 % during application and before the dry to handle time

MILD STEEL

- remove all loose material by wire brush or mechanical sander, prime with Colourthane Etch Primer or other recommended primers (refer product compatibility)

NON FERROUS METALS, STAINLESS STEEL, ZINCALUME[®] & COLORBOND[®]

- abrade using Scotch-brite pad or wet and dry sand paper. Do not use steel wool, prime with Colourthane Etch Primer or other recommended primers (refer product compatibility)

APPLICATION INSTRUCTIONS

- mixing ratio by volume 4A:1B
- mix Colourthane 500 Part A with Colourthane 500 Part B only
- induction time - none
- pot life at 25 °C 1-2 hours. Do not use after this time even if the mix is still liquid
- stir the individual components and the mixed product well using a mechanical mixer
- thinning recommendations are given as a guide and may vary depending upon substrate temperature and weather conditions
- the temperature of the mixed product must be above 15°C, otherwise extra thinner may be required to obtain application viscosity
- too much thinner will result in lower sag resistance and slower cure
- thinner should only be added after mixing the components
- freshly catalysed material should not be added to product that has been mixed for some time
- for recommendations outside those contained in this data sheet, refer to Valspar

APPLICATION METHODS

- **AIR SPRAY**
 - recommended thinnerColourthane Reducers
 - volume of thinnerup to 5 %
 - nozzle orifice approx.1.4-1.8 mm
 - nozzle pressure3.0-4.5bar (45-65 psi)
- **HIGH VOLUME LOW PRESSURE (HVLP)**
 - recommended thinnerColourthane Reducers
 - volume of thinnerup to 5 %
 - nozzle pressure0.7bar (10 psi) max
- **BRUSH/ROLLER**
 - recommended thinnerColourthane Reducers
 - volume of thinnerup to 5 %

NOTE: the maximum dry film thickness that can be achieved when brushing and rolling is 30 microns.
- **CLEANING SOLVENT**.....Colourthane Reducers

REDUCER GUIDE

Temperature	<15 °C	20 °C	25 °C	30 °C	>35 °C
Colourthane Reducer Fast	██████████				
Colourthane Reducer Standard		██████████			
Colourthane Reducer Slow				██████████	

* thinning recommendations are given as a guide and may vary depending upon substrate temperature and weather conditions

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- Use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this paint contains 0.03% monomeric diisocyanate when mixed. Provide adequate ventilation during use. Breathing the vapour is dangerous. Avoid breathing of fumes. Where applied by spray, use suitable air-fed respiratory equipment/hood at all times
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Safety Data Sheet (SDS)

ADDITIONAL DATA

Overcoating Table-

Overcoating interval for Colourthane 500 when top coating with itself

Interval	5 °C	15 °C	25 °C	35 °C	60 °C
Minimum	36 hrs	24 hrs	16 hrs	8 hrs	40 mins
Maximum	7 days	4 days	2 days	24 hrs	2 hrs

Curing Table-

Substrate Temperature	5 °C	15 °C	25 °C	35 °C	60 °C
Surface Dry	24 hrs	12 hrs	5-6 hrs	3 hrs	15 mins
Hard Dry	36 hrs	24 hrs	16 hrs	8 hrs	40 mins
Pot Life (at application viscosity)	6 hrs	3 hrs	1-2 hrs	45 mins	N/A

* adequate ventilation must be continuously maintained during application and curing

PRECAUTIONS

- for recommendations outside those contained in this data sheet, refer to Valspar

PRODUCT COMPATIBILITY

Primers

- Colourthane Etch Primer
- Colourthane NS300
- Colourthane PF330
- Epinamel UC230
- Epinamel PR250
- Epinamel PR360ZPS
- Epinamel EB600

Topcoats

- Colourthane 500

STORAGE AND PACKAGING

- shelf life at least 12 months in an unopened container
- all components shall be stored in a dry internal environment at between 5 °C and 35 °C
- packaging
 - 20 Lt kit (16 Lt Part A (when tinted), 4Lt Part B)
 - 5 Lt kit (4 Lt Part A (when tinted), 1Lt Part B)

For the most up to date information visit our website or Contact Valspar Customer Service Hotline on:

www.wattylpc.com
132 101 (Australia) or 0800 735 551 (New Zealand)



Quality ISO 9001

Valspar is committed to quality in the design, production and delivery of its products and services. Valspar's Australian manufacturing facilities quality management systems are certified to ISO9001.

Valspar's laboratory facilities are accredited for technical competence with the National Association of Tests Authorities, Australia (NATA) and comply with the requirements of ISO/IEC 17025. Accreditation No.104 (Footscray), 1154 (Glendenning) and 931 (Kilburn).



Trademarks are the property of Valspar Paint (Australia) Pty Ltd.

1. This information, provided by Valspar Paint (Australia) Pty Ltd (hereinafter referred to as "Valspar"), is important to ensure that the listed product(s) perform according to the stated application and uses and must be followed to meet Valspar's warranties express and implied. Valspar advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Valspar and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Valspar endeavours to update this information and maintain the accuracy and currency of its contents, Valspar does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, Valspar recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Valspar office before using the product(s). 4. To the full extent permitted by law, Valspar's liability for breach of a condition or warranty implied into the contract for sale between Valspar and you by law is limited at Valspar's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required Valspar Technical Services shall be contacted prior to commencement. VALSPAR PAINT (AUSTRALIA) PTY LTD (ABN 40 000 035 914)