



DESCRIPTION

- a clear, two-pack acid-catalysed sealer for interior timber

PRINCIPAL CHARACTERISTICS

- excellent sanding properties
- a high-build, low-odour sealer
- fast cure-time
- suitable for commercial and domestic applications, small and large-scale factory finishing
- suitable for interior use only

Note: We advise that you test this product to determine if it is suitable for your particular use.

COLOUR AND GLOSS

- clear, low gloss

BASIC DATA AT 25° C and 50% RELATIVE HUMIDITY

- mix ratio 9A:1B by volume
- dust free 5-10 minutes
- touch-dry 10 minutes
- sandable 1 hour
- recoat 1½ hours - better hold out is obtained if the film is left to cure overnight
- practical spreading rate 8-10 m²/L
- shelf life (cool, dry place) at least 12 months in unopened container

SURFACE PREPARATION

- all surfaces must be free from wax, silicone, oil and other contaminants
- fill holes and minor imperfections with WattyI Full Stop Timber Putty.
- sand smooth with 180-240 grade fre-cut paper, and remove all sanding dust
- if required, stain the surface using WattyI Craftsman® Dye Stain Fast, Slow or Craftsman Pigmented Stain
- Do not use Woodgrain Filler under Acid Cat Sealer

INSTRUCTIONS FOR USE

- mixing ratio by volume: 9A:1B
- induction time- none
- potlife at 25° C - 24 hours. Do not use after this time even if the mix is still liquid
- stir the components and mixed product well using a mechanical mixer
- apply a double-pass of Acid Cat Sealer to give a wet film thickness of 75 - 125 microns. Allow to dry for 1 hour then sand with 320-400 fre-cut paper, removing all sanding dust. If desired, a second coat of Acid Cat Sealer may be applied. Better hold out can be obtained if the sealer is left to dry overnight. Sand the second coat with 400 grade fre-cut paper and remove all sanding dust before applying topcoats
- finish with Acid Cat Clear Topcoat
- **Warning:** Excessive builds on timber can lead to stress-cracking as the timber adjusts to its new conditions of temperature and moisture content. The recommended maximum total build is 150 microns (dry film) for the total system. Acid Catalysed Coatings may cause discoloration in timbers eg. beech, huon pine, some cedars and cherry. This is due to a reaction between particular tannins in the timber and the acid component of the coating. Perform a test patch to check colour or use an alternative sealer such as Furniseal.
- for recommendations outside those contained in this data sheet, refer to WattyI



APPLICATION

- **CONVENTIONAL SPRAY**
 - recommended thinner Thinner L743
 - volume of thinner up to 15%
 - fluid nozzle 1.5 - 2.0 mm
 - pressure to the gun..... 250 - 350 kPa (30 - 50 psi)

- **AIR-ASSISTED AIRLESS SPRAY**
 - recommended thinner Thinner L743
 - volume of thinner up to 10%
 - fluid nozzle 0.23 - 0.28 mm (0.009 - 0.011inch)
 - pump ratio 12 - 20 : 1
 - pump pressure 7 - 10 MPa (1000 - 1500 psi)

- **HVLP CONVENTIONAL**
 - recommended thinner Thinner L743
 - volume of thinner up to 10%
 - fluid nozzle 1.5 - 2.0 mm
 - pressure to the gun..... 250 - 350 kPa (30 - 50 psi)
 - pressure to air cap 70 kPa (10 psi)

- **CLEANING SOLVENT** Thinner L743

- **Note:** In warmer conditions, replace some or all of Thinner L743 with Thinner 747 (medium) or Thinner L748 (slow).

SAFETY PRECAUTIONS

- the catalyst used with this product contains an acid component, therefore the precautions stated on the label must be followed
- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

PACKAGING

Part A 4.5 litres, 18 litres
Part B 500mL, 2 litres

For the most up to date information contact WattyI Customer Service Hotline or visit the WattyI Website.

	Australia	New Zealand
CUSTOMER SERVICE HOTLINE	132 101	0800 735 551
WEBSITE	http://www.wattyI.com.au	http://www.wattyI.co.nz

WattyI is a registered trademark of WattyI Australia Pty Ltd.

1. This information is important to ensure that the listed WattyI product(s) perform according to the stated application and uses and must be followed to meet WattyI's warranties express and implied. WattyI advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by WattyI and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While WattyI endeavours to update this information and maintain the accuracy and currency of its contents, WattyI does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, WattyI recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest WattyI office before using the product(s). 4. To the full extent permitted by law, WattyI's liability for breach of a condition or warranty implied into the contract for sale between WattyI and you by law is limited at WattyI's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required WattyI Technical Services shall be contacted prior to commencement. WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)