

**DESCRIPTION**

- an ultra premium, pre-catalysed nitrocellulose lacquer for interior timber

**PRINCIPAL CHARACTERISTICS**

- excellent feel and appearance
- superior flexibility and durability
- excellent mar resistance
- high build
- excellent abrasion-resistance
- excellent resistance to alcohol, moisture and perspiration
- specifically formulated to resist yellowing. However, because of Stylwood's initial honey colour it is not recommended for use over very pale substrates (eg. Liming white), without first testing for suitability
- designed to beautify and protect high-quality home, office and commercial woodwork, cabinets and wall panelling
- not recommended for kitchens or wet areas. Use Spectrothane or Acid Cat finishes for these locations

**Note:** We advise that you test this product to determine if it is suitable for your particular use.

**COLOUR AND GLOSS**

- clear, in a range of gloss levels (10, 30, 50, 70 and 95%)

**BASIC DATA AT 25°C and 50% RELATIVE HUMIDITY**

- dust free ..... 20 minutes
- touch-dry ..... 45 minutes
- recoat ..... 2-3 hours
- sandable ..... 1 hour
- practical spreading rate ..... 9m<sup>2</sup>/L
- shelf life (cool, dry place) ..... at least 12 months in unopened container

**SURFACE PREPARATION**

- fill holes and minor imperfections with Watty! Full Stop Timber Putty
- sand smooth with 180-240 grade fre-cut paper, and remove all sanding dust
- if required, stain the surface using Watty! Craftsman® Dye Stain Fast, Slow or Craftsman Pigmented Stain
- may be used as a self-sealer, or for easier sanding, use over Hi Seal F.S., Rediseal or Furniseal. Do not use a stearate-based sealer, as whitening of the top-coat may occur

**INSTRUCTIONS FOR USE**

- agitate contents thoroughly with flat-bladed stirrer before and during use
- apply two or preferably three coats
- may be re-coated immediately after the first coat has become dust free, but better hold-out is obtained if re-coating is left for two-three hours

**Note:** Care should be taken not to apply excessive builds in one application, otherwise surface defects may occur.

**Warning:** Excessive builds on timber can lead to stress-cracking as the timber adjusts to its new conditions of temperature and moisture content. The recommended maximum total build is 150 microns (dry film) for the total system.

- for recommendations outside those contained in this data sheet, refer to Watty!

**APPLICATION**

- **CONVENTIONAL SPRAY**
  - recommended thinner ..... L780 Industrial Universal Thinner
  - volume of thinner ..... up to 10%
  - fluid nozzle ..... 1.5 - 2.0 mm
  - pressure to the gun..... 250 - 350 kPa (30 - 50 psi)
  
- **AIR-ASSISTED AIRLESS SPRAY**
  - recommended thinner ..... L780 Industrial Universal Thinner
  - volume of thinner ..... up to 5%
  - fluid nozzle ..... 0.23 - 0.28 mm (0.009- 0.11inch)
  - pump ratio ..... 12 - 20 : 1
  - pump pressure ..... 7 - 10 MPa (1000 - 1500 psi)
  
- **HVLP CONVENTIONAL**
  - recommended thinner ..... L780 Industrial Universal Thinner
  - volume of thinner ..... up to 5%
  - fluid nozzle ..... 1.5 - 2.0 mm
  - pressure to the gun..... 250 - 350 kPa (30 - 50 psi)
  - pressure to air cap ..... 70 kPa (10 psi)
  
- **CLEANING SOLVENT** ..... L780 Industrial Universal Thinner
  
- **Note:** In warmer conditions, replace some or all of L780 Industrial Universal Thinner with Thinner L743.

**SAFETY PRECAUTIONS**

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

**PACKAGING**

4 litres, 20 litres, 200 litres

For the most up to date information contact Watty Industrial Customer Service Hotline or visit the Watty Website.

<b>CUSTOMER SERVICE HOTLINE</b>	<b>Australia</b> 132 101	<b>New Zealand</b> 0800 735 551
<b>WEBSITE</b>	<a href="http://www.watty.com.au">http://www.watty.com.au</a>	<a href="http://www.watty.co.nz">http://www.watty.co.nz</a>

Watty, Craftsman and Stylwood are a registered trademarks of Watty Australia Pty Ltd.

1. This information is important to ensure that the listed Watty product(s) perform according to the stated application and uses and must be followed to meet Watty's warranties express and implied. Watty advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Watty and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Watty endeavours to update this information and maintain the accuracy and currency of its contents, Watty does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, Watty recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Watty office before using the product(s). 4. To the full extent permitted by law, Watty's liability for breach of a condition or warranty implied into the contract for sale between Watty and you by law is limited at Watty's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required Watty Technical Services shall be contacted prior to commencement. WATTYL AUSTRALIA PTY LTD (ABN 40 000 035 914)