

DESCRIPTION

- a two pack moisture curing, zinc rich, ethyl silicate primer/finish
- approved to APAS-2908
- zinc in dry film 71% by weight

PRINCIPAL CHARACTERISTICS

- liquid A and B packs
- provides cathodic protection to steel
- anticorrosive primer for structural steel
- suitable as a system primer in various paint systems based on non-saponifiable binders
- good impact and abrasion resistance
- excellent resistance to a wide range of chemicals (refer to **I-19 Wattyl Tank Lining Resistance Guide** for a full list of suitable cargoes)
- must not be used for immersion or splash in alkaline (more than pH 9) or acidic (less than pH 5) liquids
- can withstand substrate temperatures up to 400 °C, under normal atmospheric exposure conditions
- can be used as a single coat primer/finish

COLOURS AND GLOSS

- Grey - flat

RECOMMENDED FILM THICKNESS

	Minimum	Maximum	Typical
Dry film thickness microns	60	90	75
Wet film thickness microns	92	138	115
Theoretical spreading rate m ² /l	13.0	7.2	8.7

BASIC DATA AT 25 °C / 60% Relative Humidity

- solids content approx..... 65% by volume
- mix ratio 3A:2B by volume
- touch dry after 15 minutes
- dry to handle 1 hour
- overcoating interval..... refer to overcoating table
- full cure 24 hours
- temperature resistance 400 °C (dry), 35 °C (wet)
- Zinc rich primers form zinc salts on the surface. At all times, any visible surface contamination and zinc salts must be removed before overcoating by high pressure potable water cleaning (min. 30 MPa/4000 psi), wet abrasive blasting, sweep blasting or mechanical cleaning

SURFACE PREPARATION

- all surfaces to be coated must be clean, dry and free from chalking and contamination
- oil and grease should be removed from all surfaces in accordance with AS 1627.1 solvent cleaning

MILD STEEL

- blast clean in accordance with AS 1627.4 to Sa 2½ minimum (AS 1627.9), surface profile 40-70 microns
- if oxidation occurs between blasting and application, the surface should be reblasted to the specified visual standard

- surface defects revealed by the blast cleaning process should be ground, filled or treated in the appropriate manner
- substrate temperature must be at least 5 °C during surface preparation, application and curing and at least 3 °C above dew point
- a heavily pitted steel substrate is not acceptable
- substrate temperatures ranging from 5 °C up to 40 °C are acceptable
- relative humidity should be above 60%

APPLICATION INSTRUCTIONS

- mixing ratio by volume: zinc paste to liquid binder - 3A:2B
- mix with Galvit ES510/ES600 Part B only
- induction time - none
- pot life at 25 °C 8 hours. Do not use after this time even if the mix is still liquid
- stir the paste thoroughly before adding the binder
- add gradually one third of the binder to the zinc paste
- stir thoroughly until homogeneous
- add remaining binder and continue stirring until the mixture is homogeneous
- the temperature of the mixed product should be above 15 °C
- thinner should only be added after mixing the components
- freshly catalysed material should not be added to product that has been mixed for some time
- agitate continuously during application
- Valspar recommends the use of coating inspection reports in compliance with AS/NZS 3894.10,11,12 refer to Information Sheet I-20 for more information
- for recommendations outside those contained in this data sheet, refer to Valspar

APPLICATION METHODS

- **AIRLESS SPRAY**
 - Avoid excessive film build as mud cracking may occur
 - recommended thinner Thinner L760
 - volume of thinner 0-10%
 - nozzle orifice approx. 0.48-0.64mm (0.019-0.025 inch)
 - nozzle pressure 15 MPa (2100 psi)
- **AIR SPRAY**
 - recommended thinner Thinner L760
 - volume of thinner 0-10%
 - nozzle orifice approx. 2.0mm
 - nozzle pressure 0.3 MPa (50 psi)
- **BRUSH/ROLLER**
 - For spot repair and stripe coating only
 - recommended thinner thinning not necessary
 - The maximum dry film thickness that can be achieved when brushing/rolling is 50 microns
 - Multiple coats may be required to achieve the recommended dry film thickness
- **CLEANING SOLVENT**..... Thinner L760

Note: In warmer conditions, thin with up to 10% Thinner L748 or alternatively, replace up to 50% of Thinner L760 with Mineral Turps to assist application properties

SAFETY PRECAUTIONS

- flammable. Avoid contact with heat and naked flame
- avoid contact with skin and eyes
- use gloves, mask and goggles during application
- provide adequate ventilation when using in confined spaces
- zinc paints may develop pressure on storage, open containers carefully
- provide adequate ventilation when cutting or welding this product due to harmful zinc fumes
- this product is intended for use in industrial situations by professional applicators in accordance with the advice given on this sheet. All work involving the use and application of this product should be carried out in compliance with all relevant Health, Safety & Environmental standards and regulations and must not be used without reference to the Material Safety Data Sheet (MSDS)

ADDITIONAL DATA

Surface Preparation of Galvit ES510 before overcoating

- zinc rich primers can form zinc salts on the surface and these must be removed before overcoating
- zinc rich primers should NOT be weathered for long periods before overcoating
- in Industrial and Marine Conditions, the overcoating interval should be reduced to the practical minimum
- before overcoating, zinc salts, chalking and all other forms of visible surface contamination must be removed by high pressure (30 MPa/4,000 psi) potable water cleaning, wet abrasive blasting, sweep blasting or mechanical cleaning
- to prevent zinc salt formation and surface contamination where very long overcoating intervals are required, it is recommended to overcoat Galvit ES510 within two days with Epinamel PR250

Overcoating Table

Minimum and maximum overcoating intervals with Galvit ES510

Interval	Humidity	5 °C	15 °C	25 °C	35 °C
Min	<60%	>7 days	>4 days	>48 hrs	>32 hrs
	60%	7 days	4 days	48 hrs	32 hrs
	80%	4 days	2 days	24 hrs	16 hrs
	>80%	<4 days	<2 days	<24 hrs	<16 hrs
Max	Unlimited when free from zinc salts and contamination (See surface preparation notes)				

- Galvit ES510 requires moisture for curing
- Galvit ES510 should have full cure before overcoating; relative humidity and temperature should be measured during curing to determine the overcoating time
- to reduce the curing time of Galvit ES510, allow a 4 hour flash-off time, wet the surface by spraying with fresh water and keep wet for the next 4 hours. Test for full cure after this time to determine if a further wet exposure period is required.

- curing will be retarded at low humidities. For relative humidities less than 60%, test for full cure before overcoating
- Galvit ES510 can be tested for full cure using a solvent rub test. The coated surface should be rubbed with a cloth soaked in methyl ethyl ketone for determination of cure (refer AS 3894.4/ASTM D4752)
- to avoid possible solvent popping effects (pinholes) when recoating, Galvit ES510 must be sealed with Epinamel PR250 or a thinned first coat of high solids epoxy (refer to Information Sheet I-16 for more information)

Curing and Potlife Table

Paint temperature	Humidity	5 °C	15 °C	25 °C	35 °C
Dry to Handle		5 hrs	2 hrs	1 hrs	45 mins
Full Cure	< 60%	>7 days	>4 days	>48 hrs	>32 hrs
	60%	7 days	4 days	48 hrs	32 hrs
	80%	4 days	2 days	24 hrs	16 hrs
	> 80%	<4 days	<2 days	<24 hrs	<16 hrs
Potlife (at application viscosity)			12 hrs	8 hrs	4 hrs

- adequate ventilation must be continuously maintained during application and curing

PRECAUTIONS

- for recommendations outside those contained in this data sheet, refer to Valspar

PRODUCT COMPATIBILITY

Primers

- n/a

Topcoats

- Epinamel PR250
- Epinamel EB600
- Epinamel DTS680
- Epinamel DTM985

STORAGE AND PACKAGING

- shelf life- Part A at least 6 months. Part B maximum 6 months from the date of manufacture, refer to label for expiry date
- all components shall be stored in a dry internal environment at between 5 °C and 35 °C
- packaging 12.5 Litre kit (7.5Litre Part A, 5 Litre Part B)
- product line: 201421.015 (Part A)
201433.005 (Part B)



Quality
ISO 9001

Valspar is committed to quality in the design, production and delivery of its products and services. Valspar's Australian manufacturing facilities quality management systems are certified to ISO9001.

Valspar's laboratory facilities are accredited for technical competence with the National Association of Tests Authorities, Australia (NATA) and comply with the requirements of ISO/IEC 17025. Accreditation No.104 (Footscray), 1154 (Glendenning) and 931 (Kilburn).



For the most up to date information contact Valspar Customer Service Hotline or visit the Wattyl Website.

**CUSTOMER SERVICE HOTLINE
WEBSITE**

**Australia
132 101
www.wattylpc.com**

**New Zealand
0800 735 551
www.wattylpc.com**

Trademarks are the property of Valspar Paint (Australia) Pty Ltd.

1. This information, provided by Valspar Paint (Australia) Pty Ltd (hereinafter referred to as "Valspar"), is important to ensure that the listed product(s) perform according to the stated application and uses and must be followed to meet Valspar's warranties express and implied. Valspar advises that you (a) review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) ensure that the product be used only in accordance with the information provided by Valspar and the product(s) be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (c) thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product. 2. The information in this TDS was prepared using information gathered during product development. While Valspar endeavours to update this information and maintain the accuracy and currency of its contents, Valspar does not warrant that the information provided is current when the product is used or is wholly comprehensive. 3. For all product and non-product related information, Valspar recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Valspar office before using the product(s). 4. To the full extent permitted by law, Valspar's liability for breach of a condition or warranty implied into the contract for sale between Valspar and you by law is limited at Valspar's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product. If coating rectification is required Valspar Technical Services shall be contacted prior to commencement. VALSPAR PAINT (AUSTRALIA) PTY LTD (ABN 40 000 035 914)